# Salivary Contamination and **Decontamination: Bond Strength to Dentin** of Primary and Permanent Teeth



**UNIVERSITÄT** BERN

zmk bern Zahnmedizinische Kliniken der Universität Bern

Simon Flury, Katharina Santschi, Anne Peutzfeldt, Adrian Lussi

Department of Preventive, Restorative and Pediatric Dentistry, School of Dental Medicine, University of Bern, Switzerland

Aim

To evaluate the effects of salivary contamination and decontamination on bond strength of two one-step adhesives to primary and permanent dentin.

#### Methods

Dentin specimens were prepared from extracted primary and permanent molars (210 of each) and were distributed to seven groups (n=15/group/ molar type) for each adhesive (Xeno V<sup>+</sup> and Scotchbond Universal): no saliva contamination (control); saliva contamination before or after light-curing of the adhesives followed either by air-drying, by rinsing with water and air-drying, or by rinsing with water, air-drying and reapplication of the adhesives. Resin composite was applied and the specimens were stored for 24h (37°C, 100% humidity). Then, shear bond strength (SBS) was measured and data analyzed with nonparametric ANOVA and Wilcoxon rank sum tests.

#### **Results**

Saliva contamination reduced SBS of Xeno V<sup>+</sup>, the reduction being more pronounced when contamination occurred before light-curing than after. In both situations, decontamination involving reapplication of the adhesive restored SBS. Saliva contamination had no significant effect on Scotchbond Universal. There were no differences in SBS between primary and permanent teeth.

### Conclusion

Saliva contamination reduced SBS of Xeno V<sup>+</sup>, but not of Scotchbond Universal. SBS was restored when contaminated dentin was rinsed with water and air-dried followed by reapplication of the adhesive.

#### Acknowledgements

The authors would like to thank G. Fischer, Institute of Mathematical Statistics and Actuarial Science, University of Bern, for the statistical analysis and I. Badertscher, School of Dental Medicine, University of Bern, for the preparation of this poster.

## Xeno V<sup>+</sup> (X) or Scotchbond Universal (S)



Flowchart of the adhesive treatments resulting in seven groups for each adhesive.



Shear Bond Strength (MPa) of Primary Molars (n = 15) for Groups 1X/1S to 7X/7S  $(X = Xeno V^+, S = Scotchbond Universal).$ 

Shear Bond Strength (MPa) of Permanent Molars (n = 15) for Groups 1X/1S to 7X/7S  $(X = Xeno V^+, S = Scotchbond Universal).$