

# Hierarchical self-assembly of the DNA-grafted supramolecular polymers

Yuliia Vyborna<sup>1</sup>, Robert Häner\*<sup>1</sup>

<sup>1</sup> Department of Chemistry and Biochemistry, University of Bern Freiestrasse 3, CH-3012 Bern, Switzerland.


Email: yuliia.vyborna@dcb.unibe.ch

Conjugation of functional entities with a specific set of optical, mechanical or biological properties to DNA strands allows engineering of sophisticated DNA-containing architectures.<sup>[1]</sup>

<sup>[2]</sup> Among various hybrid systems, DNA-grafted polymers occupy an important place in modern materials science.<sup>[3]</sup> In this contribution we present the non-covalent synthesis and properties of DNA-grafted linear supramolecular polymers (SPs), which are assembled in a controllable manner from short chimeric DNA-pyrene oligomers. The synthetic oligomers consist of two parts: a 10 nucleotides long DNA chain and a covalently attached segment of variable number of phosphodiester-linked pyrenes. The temperature-dependent formation of DNA-grafted SPs is described by a nucleation-elongation mechanism.

The high tendency of pyrenes to aggregate in water, leads to the rapid formation of SPs. The core of the assemblies consists of stacked pyrenes. They form a 1D platform, to which the DNA chains are attached. Combined spectroscopic and microscopic studies reveal that the major driving forces of the polymerization are  $\pi$ -stacking of pyrenes and hydrophobic interactions, and DNA pairing contributes to a lesser extent.<sup>[4]</sup> AFM and TEM experiments demonstrate that the 1D SPs appear as elongated ribbons with a length of several hundred nanometers. They exhibit an apparent helical structure with a pitch-to-pitch distance of  $50 \pm 15$  nm.

Since DNA pairing is a highly selective process, the ongoing studies are aimed to utilize DNA-grafted SPs for the programmable arrangement of functional entities. For example, the addition of non-modified complementary DNA strands to the DNA-grafted SPs leads to the cooperative formation of higher-order assemblies. Also, our experiments suggest that the fluorescent pyrene core of 1D ribbons serves as an efficient donor platform for energy transfer applications.



## Acknowledgements

We thank Dr. Alexander Rudnev and Mykhailo Vybornyi for helpful discussions.

## References

- [1] T. Aida, E. Meijer, S. Stupp, *Science* **2012**, *335*, 813–817
- [2] C. K. McLaughlin, G. D. Hamblin, H. F. Sleiman, *Chemical Society Reviews* **2011**, *40*, 5647–5656.
- [3] Peng, L.; Wu, S.; You, M.; Han, D.; Chen, Y.; Fu, T.; Tan, W. *Chem. Sci.* **2013**, *4*, 1928.
- [4] Vybornyi, M.; Rudnev, A. V.; Langenegger, S. M.; Wandlowski, T.; Calzaferri, G.; Häner, R. *Angew. Chem., Int. Ed.* **2013**, *52*, 11488.