

RESEARCH ARTICLE

Analyses of the Erosive Effect of Dietary Substances and Medications on Deciduous Teeth

Adrian Lussi*, Thiago Saads Carvalho

Department of Preventive, Restorative and Pediatric Dentistry, University of Bern, Bern, Switzerland

* adrian.lussi@zmk.unibe.ch

Abstract

This study aimed at analysing the erosive potential of 30 substances (drinks, candies, and medicaments) on deciduous enamel, and analyse the associated chemical factors with enamel dissolution. We analysed the initial pH, titratable acidity (TA) to pH 5.5, calcium (Ca), inorganic phosphate (P_i), and fluoride (F) concentration, and degree of saturation ((pK - pI)_{HAP}, (pK - pI)_{FAP}, and (pK - pI)_{CaF₂}) of all substances. Then, we randomly distributed 300 specimens of human deciduous enamel into 30 groups (n = 10 for each of the substances tested). We also prepared 20 specimens of permanent enamel for the sake of comparison between the two types of teeth, and we tested them in mineral water and Coca-Cola[®]. In all specimens, we measured surface hardness (VHN: Vickers hardness numbers) and surface reflection intensity (SRI) at baseline (SH_{baseline} and SRI_{baseline}), after a total of 2 min (SH_{2min}) and after 4 min (SH_{4min} and SRI_{4min}) erosive challenges (60 ml of substance for 6 enamel samples; 30°C, under constant agitation at 95 rpm). There was no significant difference in SH_{baseline} between deciduous and permanent enamel. Comparing both teeth, we observed that after the first erosive challenge with Coca-Cola[®], a significantly greater hardness loss was seen in deciduous (-90.2±11.3 VHN) than in permanent enamel (-44.3±12.2 VHN; p = 0.007), but no differences between the two types of teeth were observed after two challenges (SH_{4min}). After both erosive challenges, all substances except for mineral water caused a significant loss in relative surface reflectivity intensity, and most substances caused a significant loss in surface hardness. Multiple regression analyses showed that pH, TA and Ca concentration play a significant role in initial erosion of deciduous enamel. We conclude that drinks, foodstuffs and medications commonly consumed by children can cause erosion of deciduous teeth and erosion is mainly associated with pH, titratable acidity and calcium concentration in the solution.

Introduction

Dental erosion is the acid dissolution of dental hard tissues caused by multiple factors. One of these factors are acidic substances in the diet (nutrition-related factors) [1]. Erosion can occur



OPEN ACCESS

Citation: Lussi A, Carvalho TS (2015) Analyses of the Erosive Effect of Dietary Substances and Medications on Deciduous Teeth. PLoS ONE 10(12): e0143957. doi:10.1371/journal.pone.0143957

Editor: Brian Lee Beatty, New York Institute of Technology College of Osteopathic Medicine, UNITED STATES

Received: April 22, 2015

Accepted: November 11, 2015

Published: December 23, 2015

Copyright: © 2015 Lussi, Carvalho. This is an open access article distributed under the terms of the [Creative Commons Attribution License](https://creativecommons.org/licenses/by/4.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

Data Availability Statement: The data underlying the findings are fully available and all relevant data are presented within the manuscript.

Funding: This study was funded by the Deutsche Gesellschaft für Zahnerhaltung (DGPZM-Wissenschaftsfonds) to AL and TSC.

Competing Interests: The authors have declared that no competing interests exist.

in both deciduous and permanent teeth [2–5]. It starts with a softening of the tooth surface (enamel) and progresses to extensive loss of tooth substance when contact with the acids continues [6–8]. Various dietary substances and medicaments have been associated with dental erosion [9–15], and many studies have investigated which chemical factors are most significantly associated with enamel dissolution [16–23]. However, many studies have focused on permanent teeth, and more detailed investigations should be carried out to find out the effect of different dietary substances on deciduous enamel, and which chemical factors will play a role on erosive demineralization of these teeth.

Deciduous enamel is histologically different to permanent enamel. Basically, prism arrangements in deciduous and permanent enamel are similar [24], but the prisms in deciduous enamel are smaller, with more complete boundaries, and are more widely spread than those in permanent enamel [25]. Also, the prisms in deciduous enamel are more gently curved, and have slightly less pronounced Hunter-Schreger bands [25]. Deciduous enamel is considerably less mineralized [26], has greater total carbonate content [27], and a higher organic content [28] than permanent enamel. These histological differences could also lead to different erosion patterns in deciduous and permanent enamel, so it is important to fully investigate the effect of different dietary substances on deciduous enamel.

Moreover, in a study by Ganss et al. [29], children who initially presented with erosive lesions in deciduous teeth had a significantly greater risk (3.9-fold) of having erosive lesions in their permanent teeth. Similar results were also reported by Harding et al. [30], who showed that 5-year-old children who present with severe erosive tooth wear in deciduous teeth are 5 times more likely to present erosive tooth wear in permanent teeth at the age of 12 years. It is, thus, suggested that tooth wear in deciduous teeth ought to be regarded as a predictive factor for wear in permanent teeth, and health professionals should be fully aware of the erosive effect of different dietary substances on deciduous enamel in order to be able to give children and parents the best oral health recommendations. Consequently, the aim of this study was to analyse the potential of different substances to cause erosion of deciduous enamel, and to determine which chemical factors are most strongly associated with enamel dissolution in deciduous teeth.

Material and Methods

Preparation of enamel specimens

From a pool of extracted teeth, we randomly selected 150 caries-free human deciduous molars and 20 (permanent) premolars. The teeth were extracted by dental practitioners in Switzerland. Before the extraction, the patients and their parents were informed about the use of their teeth for research purposes and their oral consent was obtained. Because we are using teeth from a pooled bio-bank, the local ethics committee categorized the samples as “irreversibly anonymised”, and no previous approval was necessary. The crowns of all teeth were separated from the roots, and cut in two halves (into buccal and lingual surfaces). The enamel slabs were embedded in acrylic resin blocks (Paladur[®], Bad Homburg, Germany) using two planar parallel moulds of 8 mm and 0.2 mm. The latter mould was removed and the blocks were then serially ground (LaboPol-21 rotating polishing machine, Struers, Ballerup, Denmark) with silicon carbide paper discs (grade 18 μm for 30 s, 8 μm grade for 30 s, 5 μm grade for 1 min, 3 μm diamond abrasive paste for 1 min), removing 200 μm of enamel from each specimen. After each polishing step, the resin blocks were rinsed and sonicated for 2 min in tap water and all specimens were then stored in a saturated mineral solution (1.5 mM CaCl_2 , 1.0 mM KH_2PO_4 , 50 mM NaCl, pH 7.0 [31]) until the time of the experiment. The 300 deciduous enamel samples

were randomly distributed into 30 groups ($n = 10$ for each of the substances tested). The permanent enamel samples were divided into two groups ($n = 10$).

Substances tested

In the present study, we tested 30 substances, ranging from drinks, candies, and medicaments frequently used by children and young adolescents (Table 1). For the experiment, all carbonated drinks, candies, and medicaments were pre-treated as follows. The carbonated drinks were degassed by stirring at room temperature (10 min). The candy was dissolved in deionized water (5.2 g candy / 10 ml water), under constant mixing at 45°C; the resulting candy solution was then cooled and used at 30°C for the experiments. The medicaments and concentrated drinks were all prepared with deionized water according to the manufacturer's instructions. The chewing gum was ground for 5 min (2 g chewing gum in 10 ml of deionized water) using a mortar and pestle, and the resulting solution was used in the experiment. The fruits were squeezed/crushed and the juice was then passed through a sieve (1.0 x 1.0 mm).

Chemical analysis of the substances

For the chemical analyses [22], we used 10 g of each solution at 30°C to measure the initial pH and the titratable acidity to pH 5.5 (total amount of base needed to raise the pH of the substance to 5.5). An automatic titrator (Toledo DL 53, Mettler Toledo, Electrode DG 101-SC, Software: LabX pro, Schwerzenbach, Switzerland) established the initial pH of the solutions, which were then individually titrated with 0.5 mol/l NaOH in steps of 0.02 ml [23]. Titratable acidity was calculated as the amount of base (mmol/L of sample) required to raise the pH to 5.5. Calcium (Ca) concentration was measured with the standard atomic absorption method, using an atomic absorption spectrometer with an air/acetylene flame. Lanthanum was added to all the products and standards (final end concentration 0.2%) to suppress interference from inorganic phosphates (P_i). Total P_i concentration was analysed by the ammonium molybdate method of Chen et al. (1956) [32]. Fluoride (F) concentration was determined using an F ion-specific electrode (Orion 960900, Boston, MA, USA). Before F measurement, we added total ionic strength adjustment buffer (TISAB) to all products and standard solutions (1:1 ratio), without previously neutralizing the substances. The concentrations of Ca and P_i are expressed in mmol/l and those of F in ppm. The degree of saturation ($pK-pI$) with respect to hydroxyapatite (HAP), fluorapatite (FAP), and calcium fluoride (CaF_2) was calculated from the pH and the concentrations of Ca, P_i and F using a computer program [33]. This program assumes a solubility product for HAP of $10^{-58.5}$ and for FAP of $10^{-59.6}$ [34, 35]. The concentrations of Ca, P_i and F, the pH, and the titratable acidity were measured in duplicate.

Surface hardness measurement

The present method describes hardness measurements using nanoindentations. Surface hardness (SH) of each enamel specimen was determined with a Vickers diamond under a pressure of 50 mN for 15 s (Fischerscope HM 2000 XYp; Helmut Fischer, Hünenberg, Switzerland). A total of six baseline indentations were made at intervals of 50 μ m. Further indentations next to the previous indentations were made following the experimental procedure. Vickers hardness was automatically calculated from the depth of the indentations by the computer program. The load resolution was ≤ 0.04 mN and the indentation depth was 600 nm for sound enamel and < 1000 nm for most softened specimens. The device allowed fully automatic measurements using a programmable x, y stage. The WIN-HCU software calculated SH. The SH value for each enamel slab was determined by calculating the average of six indentations.

Table 1. Basic information on the substances tested and their chemical parameters: pH, titratable acidity to pH 5.5 (mmol OH⁻/l to pH 5.5), calcium [Ca], inorganic phosphate [P_i], and fluoride [F] concentrations, degree of saturation with respect to hydroxyapatite ((pK-pI)_{HAP}), with respect to fluorapatite ((pK-pI)_{FAP}), and with respect to calcium fluoride ((pK-pI)_{CaF₂}).

Substance	Brand name/ producer	Flavour	Erosion- related ingredients*	pH	mmol OH ⁻ /l to pH 5.5	[Ca] (mmol/l)	[P _i] (mmol/l)	[F] (ppm)	(pK-pI) _{HAP}	(pK-pI) _{FAP}	(pK-pI) _{CaF₂}
MINERAL WATER											
Mineral water	Valsér [®] , Coca-Cola Company	–	–	6.53	–	10.57	< 0.01	0.58	-0.35	3.47	-0.82
SOFT DRINKS											
Coca-Cola [®]	Coca-Cola [®] , Coca-Cola Company	Cola	Phosphoric acid, carbonic acid,	2.55	9.32	0.53	5.39	0.05	-20.59	-14.31	-5.45
Pepsi Cola [®]	Pepsi Cola [®] , PepsiCo	Cola	Phosphoric acid, citric acid, carbonic acid, and flavours	2.51	8.30	0.22	5.38	<0.05	-22.83	-17.09	-7.00
Fanta [®] Regular	Fanta [®] , Coca-Cola Company	Orange	Orange fruit, citric acid, carbonic acid, and flavours	2.59	36.19	0.56	0.14	<0.05	-24.76	-18.65	-5.64
Sprite [®]	Sprite [®] , Coca-Cola Company	Lemon	Carbonic acid, citric acid, acidity regulator, and flavours	2.57	31.56	0.47	< 0.01	<0.05	-34.71	-28.78	-6.12
Guaraná Antártica [®]	Antártica	Guaraná	Citric acid and carbonic acid	2.62	15.55	0.03	< 0.01	<0.05	-36.96	-31.02	-7.21
Rivella [®] Red	Rivella	NA	Milk serum, carbonic acid, citric acid, and flavours	3.28	32.88	2.95	2.72	0.07	-12.52	-6.41	-3.61
Ice tea	NA, Coop (supermarket in Switzerland)	NA	Black tea extract, citric and ascorbic acids	2.43	24.36	0.03	0.06	0.88	-33.58	-26.06	-4.45
Ice tea peach	Lipton, Unilever	Peach	Black tea extract and peach juice	2.65	25.15	0.08	0.13	0.55	-28.39	-21.12	-4.01
FRUITS, JUICES AND SMOOTHIES											
Kiwi (fruit)	NA	NA	NA	3.24	159.81	1.06	3.40	<0.05	-14.53	-9.93	-7.12
Orange (fruit)	NA	NA	NA	3.93	71.93	1.50	1.18	<0.05	-10.22	-5.22	-4.77
Orange juice	Hohes C, Eckes AG	Orange	Orange juice	3.63	83.56	2.11	1.58	<0.05	-11.32	-5.89	-4.38
Apple juice	Ramseier Premium, Ramseier Suisse AG	Apple	Apple juice and pear juice	3.24	70.30	1.17	1.62	<0.05	-15.23	-9.44	-4.68
Apple juice for babies	Nestlé	Apple and pear	Apple juice, pear juice, vitamin C	3.59	48.19	2.55	1.96	0.17	-10.98	-4.70	-2.68
Ribena [®]	Lucozade Ribena Suntory	Blackcurrant	Blackcurrant juice concentrate, citric acid, and vitamin C	2.51	27.94	0.36	0.17	0.01	-26.06	-20.42	-6.93

(Continued)

Table 1. (Continued)

Substance	Brand name/ producer	Flavour	Erosion- related ingredients*	pH	mmol OH ⁻ /l to pH 5.5	[Ca] (mmol/l)	[P _i] (mmol/l)	[F] (ppm)	(pK-pI) _{HAP}	(pK-pI) _{FAP}	(pK-pI) _{CaF₂}
Fruit smoothie	innocent	Kiwi, apple and limes	Apple juice, grape juice, kiwi juice, lime juice, and pineapple juice	3.27	82.44	2.10	0.27	<0.05	-16.13	-10.62	-4.94
YOGHURT											
Forest berries yoghurt	NA, Migros (Supermarket in Switzerland)	Berries	Forest Berries;	4.13	62.86	37.39	10.72	<0.05	-0.55	4.63	-2.86
SOUR CANDIES											
Candy spray	Mega Mouth [®] Candy Spray, Bazooka Candy Brands International Ltd	NA	Citric acid	2.14	441.75	0.12	0.16	<0.05	-31.67	-26.76	-9.65
Sour candy	Haribo [®] Pommes, Haribo GmbH & Co., Germany	Apple	Citric, malic, and tartaric acids	2.46	88.10	0.07	0.12	<0.05	-30.57	-24.64	-7.18
Sour chewing gum	Trident [®] Senses, Modelez	Mega Mystery	Citric acid, malic acid	2.74	22.57	0.37	0.03	<0.05	-26.56	-21.57	-7.76
SPORTS AND ENERGY DRINKS											
Monster Energy Drink [®]	Monster Energy Drink [®] , Vertrieb Spar GmbH, Austria	NA	Citric, sorbic, carbonic, and benzoic acids, vitamin B, taurine	3.35	62.39	0.07	0.03	<0.05	-25.05	-19.38	-5.82
Red Bull [®] Energy Drink	Red Bull [®] , Red Bull GmbH, Austria	NA	Sodium citrate, carbonic acid, taurine, vitamin B	3.35	67.76	1.41	< 0.01	0.13	-25.72	-19.38	-3.27
Gatorade [®]	Gatorade [®] , PepsiCo	NA	Citric acid, flavours	2.89	37.38	0.05	2.98	0.05	-23.94	-17.74	-5.97
MEDICAMENTS											
Dafalgan [®] syrup for children	Bristol-Myers Squibb	NA	NA	5.26	7.91	0.07	< 0.01	<0.05	-15.16	-11.65	-6.37
Mucosolvon [®] for children	Boehringer Ingelheim	NA	Benzoic acid	3.13	14.43	0.01	0.01	<0.05	-31.47	-26.41	-8.21
Fluimucil [®] Effervescent	Zambon Schweiz	NA	NA	4.48	14.04	0.01	< 0.01	<0.05	-29.35	-25.55	-8.26
Tossamin [®] sugar free syrup	Novartis Consumer Health Schweiz	NA	Sorbic acid	4.43	19.46	0.01	1.46	<0.05	-16.42	-12.59	-8.12
Ventolin [®] syrup	Glaxo Smith Kline	NA	NA	3.19	56.08	0.02	< 0.01	<0.05	-36.98	-32.35	-8.85
Claritin [®] syrup	MSD Merk Sharp & Dohme AG	NA	Peach aroma	2.98	74.34	0.07	< 0.01	<0.05	-37.13	-32.23	-8.74

(Continued)

Table 1. (Continued)

Substance	Brand name/ producer	Flavour	Erosion- related ingredients*	pH	mmol OH ⁻ /l to pH 5.5	[Ca] (mmol/l)	[P _i] (mmol/l)	[F] (ppm)	(pK-pI) _{HAP}	(pK-pI) _{FAP}	(pK-pI) _{CaF₂}
Maltofer [®] syrup	Vifor (International) AG	NA	NA	4.90	5.48	0.12	< 0.01	<0.05	-20.68	-17.47	-7.45

* Erosion-related ingredients are those listed on the packaging of each substance.

NA = not available.

When [P_i] values were <0.01mmol/l, exact values of 0.0001 mmol/l were used in the (pK-pI) calculations.

doi:10.1371/journal.pone.0143957.t001

Surface reflection intensity

For the surface reflection intensity (SRI) measurements, we used a recently developed table-top reflection device [36–38]. The device was connected to a computer running a specific software that registers the point of highest reflection intensity, which is expressed as a SRI value. We measured SRI initially (SRI_{baseline}) and after the second challenge (SRI_{4min}), and from these SRI values, we calculated the relative percentage decrease in reflection intensity (rSRI) using the formula $rSRI_i = (100 \times (SRI_{4min} - SRI_{baseline})) / SRI_{baseline}$. In practical terms, more negative rSRI values represent greater decrease in reflection intensity, which, in turn, represent more erosion of the enamel surface.

Study design

Immediately prior to the experimental procedures, the resin blocks were further polished with 1 µm diamond abrasive for 1 min (LaboPol-6, DP-Mol Polishing, DP-Stick HQ; Struers, Copenhagen, Denmark) to ensure the removal of possible remnants from storage. Initially, the samples were incubated in freshly collected human saliva (20 ml / 6 enamel samples, 3 h, 37°C, under constant shaking). For that, stimulated saliva was collected from one healthy adult donor (stimulated salivary flow rate 2.32 ml/min) by chewing on a piece of paraffin pellets (Fluka; Sigma-Aldrich Chemie GmbH, Munich, Germany) for 30 min. An approval from the institutional review board is not necessary for collecting saliva samples, so the local Ethical Committee (Kantonale Ethikkommission) waived the need for ethical approval. In the eyes of the Ethical Committee, when collecting saliva samples, we are only required to obtain the consent from the saliva expeditor, which can be done verbally. In our study, the saliva donor gave a verbal consent, since written consent was not required. The saliva was collected in an ice-cooled tube at least 1 h after the donor had consumed any food or drink [39, 40]. The samples were then carefully rinsed with tap water (50 s) and with deionized water (10 s), then dried with oil-free air (5 s). All enamel samples had their baseline SH and SRI individually measured (SH_{baseline} and SRI_{baseline}), after which they were subjected to two consecutive erosive challenges. Each erosive challenge consisted of individually immersing the specimens into the respective test substance (10 ml / sample) for 2 min at 30°C, under constant agitation (95 rpm). The samples were then taken out of the solution, washed (10 s) and dried (5 s), and a second SH measurement was performed (SH_{2min}). Subsequently, the samples were submitted to another erosive challenge (2 min), rinsed, dried, and a final SH and SRI measurement was carried out (SH_{4min} and SRI_{4min}). A total of 10 deciduous enamel specimens were tested per substance (5 buccal and 5 lingual surfaces randomly chosen). In addition, the two groups

containing the permanent enamel samples were also submitted to the same experimental protocol, and were treated with mineral water (n = 10) or Coca-Cola® (n = 10).

Statistical analyses

Wilcoxon's signed rank tests were used to compare the SH and SRI values before and after immersion in the respective drink or solution. Changes in SH (Δ SH) were calculated as follows: for the first 2-min erosive challenge Δ SH₂₋₀ = SH_{2min} - SH_{baseline}; for the second 2-min erosive challenge Δ SH₄₋₂ = SH_{4min} - SH_{2min}; and for the total 4-min erosive challenge Δ SH₄₋₀ = SH_{4min} - SH_{baseline}. Associations between the changes in SRI (rSRI, denoted as dependent variable), Δ SH (denoted as the dependent variable) and pH, titratable acidity, and Ca, P_i and F concentrations, HAP saturation, FAP saturation, CaF₂ saturation (independent variables) were investigated using Spearman's Correlation Coefficients. Since HAP and FAP saturation are not independent of pH, titratable acidity, and Ca, P_i and F concentrations, care was taken not to include them in the regression analyses. Multiple linear regression analyses were carried out to verify the association of Δ SH₂₋₀ and Δ SH₄₋₀ with pH, titratable acidity, Ca, Pi and F concentrations. Association between Δ SH₄₋₀ and rSRI were investigated using spearman's correlation coefficient and linear regression analysis. Furthermore, additional differences between deciduous and permanent enamel were verified using the Mann-Whitney U test. The significance level was set at 0.05 for all analyses.

Results

[Table 1](#) presents the 30 substances and their chemical parameters. The SH values at baseline (SH_{baseline}), the mean SH loss (Δ SH) after the first (Δ SH₂₋₀) and second (Δ SH₄₋₂) erosive challenges, as well as the relative surface reflection intensity, are presented in [Table 2](#). Most of the substances caused a significant decrease in SH after the first erosive challenge (p < 0.05), with the exception of mineral water (negative control), ice tea peach, apple juice for babies, and some medicaments. Interestingly, during the second erosive challenge, only mineral water, yogurt and some medicaments caused no further loss of SH. After both erosive challenges, all substances caused significant loss in relative surface reflectivity intensity, except for mineral water ([Table 2](#)). There was a significant correlation (p < 0.001; $\rho = 0.66$) between loss in surface hardness (Δ SH₄₋₀) and relative percentage decrease in reflection intensity (rSRI; [Fig 1](#)), with regression [Eq \(1\)](#) fitting the data:

$$rSRI = -46.9 + 0.18 \times \Delta SH_{4-0} \quad (1)$$

By far the most erosive substance was candy spray, which caused a loss of SH of more than 300 Vickers Hardness Numbers after the first erosive challenge, and caused the greatest relative change in SRI with a decrease of more than 95% in the SRI of the samples. Kiwi fruit caused the greatest decrease in SH during the second erosive challenge. Regarding the chemical parameters, we see that candy spray had the lowest pH and the highest titratable acidity, whereas kiwi exhibited the second-highest titratable acidity.

Analysing the effect of the different chemical properties of the drinks on dental erosion in deciduous enamel, we see that pH showed a moderate positive correlation with Δ SH and rSRI, whereas all other parameters showed a weak correlation ([Table 3](#)). This was also shown by the results of the multivariate linear regression analyses ([Table 4](#)), where, despite the weak correlation values observed in [Table 3](#), not only pH, but also titratable acidity, Ca concentration, and, to a lesser extent, Pi concentration all play a role in initial enamel erosion. [Table 4](#) shows that

Table 2. Mean and standard error of the mean (SEM) for surface hardness at baseline ($SH_{baseline}$), the difference in surface hardness between baseline and the first erosive challenge (ΔSH_{2-0}), the difference in surface hardness between the first and the second erosive challenges (ΔSH_{4-2}), and the relative difference in surface reflection intensity between baseline and the second erosive challenge ($rSRI_{4-0}$).

	$SH_{baseline}$		ΔSH_{2-0}			ΔSH_{4-2}			$rSRI_{4-0}$		
	Mean	SEM	Mean	SEM	p-value	Mean	SEM	p-value	Mean	SEM	p-value
MINERAL WATER											
Mineral water	509.5	19.6	-5.0	7.7	0.695	-6.1	5.5	0.375	15.6	11.0	0.301
SOFT DRINKS											
Coca-Cola®	501.0	12.7	-90.2	11.3	0.002	-79.1	10.3	0.002	-83.0	2.0	0.002
Pepsi-Cola®	497.6	10.3	-60.7	7.6	0.002	-86.4	8.8	0.002	-87.7	1.2	0.004
Fanta® Regular	491.2	10.9	-100.6	9.8	0.002	-105.1	14.8	0.002	-85.8	1.5	0.002
Sprite®	511.0	13.0	-124.4	4.7	0.002	-134.1	8.2	0.002	-85.3	1.4	0.002
Guaraná Antártica®	502.5	14.4	-32.3	8.6	0.014	-58.5	7.8	0.002	-77.1	2.1	0.002
Rivella® Red	491.1	14.2	-44.8	15.0	0.002	-112.9	11.9	0.002	-78.1	2.3	0.002
Ice tea	500.8	10.5	-63.7	5.4	0.002	-84.1	8.4	0.002	-82.8	2.5	0.004
Ice tea Peach	483.6	10.0	-25.5	11.2	0.106	-101.2	9.8	0.002	-82.2	1.6	0.004
FRUITS, JUICES AND SMOOTHIES											
Kiwi (fruit)	498.9	10.3	-60.8	15.9	0.004	-142.3	13.5	0.002	-94.3	1.9	0.002
Orange (fruit)	502.0	11.5	-16.2	5.1	0.014	-43.4	7.3	0.002	-60.7	2.1	0.004
Orange juice	499.4	13.3	-19.2	5.2	0.006	-30.0	5.6	0.002	-72.4	6.1	0.002
Apple juice	480.2	7.6	-37.5	13.6	0.027	-107.4	17.7	0.004	-93.4	1.1	0.002
Apple juice for babies	494.6	9.8	-15.4	7.6	0.065	-48.6	6.0	0.002	-71.0	3.7	0.004
Ribena®	506.8	11.3	-50.1	7.0	0.002	-91.4	14.8	0.004	-84.6	2.1	0.002
Fruit smoothie	532.6	15.5	-38.8	10.8	0.006	-77.2	5.3	0.002	-71.6	3.2	0.002
YOGHURT											
Forest berries yoghurt	494.5	6.2	24.7	11.4	0.037	1.6	12.8	0.922	-23.9	7.6	0.006
SOUR CANDIES											
Candy spray	509.9	13.1	-301.7	11.3	0.002	-110.7	12.5	0.002	-97.2	2.4	0.004
Sour candy	525.7	9.0	-74.1	14.3	0.002	-110.7	15.1	0.002	-84.0	2.3	0.002
Sour chewing gum	490.3	13.6	-53.9	7.0	0.002	-81.5	6.7	0.002	-80.7	1.6	0.002
SPORTS AND ENERGY DRINKS											
Monster Energy Drink®	509.9	14.9	-51.6	6.7	0.002	-77.1	14.0	0.004	-75.4	2.1	0.002
Red Bull® Energy Drink	515.5	15.3	-52.6	9.3	0.004	-92.2	8.7	0.002	-74.9	2.4	0.002
Gatorade®	541.8	18.4	-115.4	20.2	0.002	-89.1	9.2	0.002	-71.7	3.0	0.002
MEDICAMENTS											
Dafalgan syrup	478.9	13.1	17.1	8.4	0.049	18.7	15.6	0.232	-20.6	6.1	0.006
Mucosolvon cough syrup	520.1	13.7	-7.8	9.2	0.625	-41.6	7.5	0.002	-69.9	3.8	0.002
Fluimucil effervescent	496.4	6.8	-11.9	4.7	0.020	-36.1	2.6	0.002	-46.4	4.3	0.006
Tossamin sugar free syrup	510.5	10.3	15.8	14.0	0.492	-13.5	10.6	0.193	-49.5	6.7	0.004
Ventolin syrup	512.9	9.4	-54.2	5.9	0.002	-85.3	6.7	0.002	-74.0	3.7	0.004
Claritine syrup	527.9	15.9	-10.8	5.8	0.106	-13.8	6.4	0.065	-40.8	3.5	0.002
Maltofer syrup	501.7	8.2	9.9	5.7	0.131	-5.4	6.1	0.432	-19.8	4.3	0.002

doi:10.1371/journal.pone.0143957.t002

lower pH values and Ca concentration, and higher titratable acidity values are significantly related to more loss of SH during erosion.

Comparing permanent enamel with deciduous enamel treated with the same substances (Table 5), we observed no significant differences in initial hardness between the two kinds of teeth. However, a significant difference was observed in the change in SH when the samples were immersed in Coca-Cola®. After the first erosive challenge (ΔSH_{2-0}), deciduous enamel




Fig 1. Association between relative surface reflection intensity (rSRI) and change in surface hardness (ΔSH_{4-0}). The solid line represents the regression line (Eq 1).

doi:10.1371/journal.pone.0143957.g001

exhibited significantly greater hardness loss (-90.2 ± 11.3 VHN) than permanent enamel (-44.3 ± 12.2 VHN; $p = 0.007$). However, no differences between the two types of teeth were observed in the total change in SH after both challenges (ΔSH_{4-0}), or in the surface reflection intensity.

Discussion

Despite the great number of studies on dental erosion, there is still a lack of information regarding the erosive dissolution of deciduous teeth. In the present study, we show the erosive effect of various substances on deciduous enamel. Moreover, we analysed the effect of different chemical factors on the initial erosion process in deciduous teeth. In line with the previous studies, we observed that several soft drinks, fruit juices and smoothies, sour candies, and medicaments can cause significant erosion. This is not surprising given their degree of saturation with respect to HAP and FAP.

Dental enamel is mostly made up of calcium (Ca^{2+}), phosphate (PO_4^{3+}), hydroxide (OH^-), and, to a lesser extent, fluoride (F^-) ions [41]. In the oral cavity, the teeth are surrounded by

Table 3. Spearman’s correlation coefficients between the chemical properties of the substances and the difference in surface hardness between baseline and the first erosive challenge (ΔSH_{2-0}), the total difference in surface hardness after all erosive challenges (ΔSH_{4-0}), and the relative difference in surface reflection intensity between baseline and the second erosive challenge ($rSRI_{4-0}$).

	ΔSH_{2-0}	ΔSH_{4-0}	$rSRI_{4-0}$
pH	0.635***	0.667***	0.644***
Titrateable acidity	-0.197***	-0.275***	-0.256***
[Ca]	-0.018	-0.094	-0.155**
[P _i]	-0.094	-0.158**	-0.273***
[F]	-0.165**	-0.232***	-0.126*
(pK-pI) _{HAP} [‡]	0.306***	0.268***	0.153*
(pK-pI) _{FAP} [†]	0.289***	0.245***	0.119*
(pK-pI) _{CaF₂} [‡]	0.029	-0.033	-0.061

[Ca], [P_i], [F]: calcium, phosphate and fluoride concentrations, respectively;

* significant at p<0.05;

** significant at p<0.005;

*** significant at p<0.001;

‡ Degree of saturation with respect to hydroxyapatite;

† Degree of saturation with respect to fluorapatite.

‡ Degree of saturation with respect to CaF₂.

doi:10.1371/journal.pone.0143957.t003

saliva, and the enamel crystals are in a constant equilibrium with the saliva. In other words, there is a continuous exchange of Ca²⁺, PO₄³⁺, OH⁻, and F⁻ between saliva and enamel. When the teeth are exposed to substances that have a low concentration of these ions, there is a tendency for enamel to release more of these ions to the environment in order to attain a new state of equilibrium [41]. Acidic substances with low pH values can exacerbate this process and lead to further demineralization. Therefore, the solubility of enamel is highly dependent on the pH of the surrounding substance, as well as the substance’s Ca²⁺, PO₄³⁺, and (to a lesser extent) F⁻ concentrations [12, 16, 17, 42–44]. These parameters are, therefore, used to calculate the degree of saturation (pK-pI) of the substances with respect to hydroxyapatite (HAP) and fluorapatite (FAP) [33].

The degree of saturation values essentially indicate whether a substance is more or less likely to cause dissolution of enamel. When a substance has (pK-pI)_{HAP} and (pK-pI)_{FAP} values below zero, it is said that the substance is undersaturated with respect to HAP and FAP, and this will cause enamel to dissolve until equilibrium is reached. However, if the substance has positive (pK-pI)_{HAP} and (pK-pI)_{FAP} values, it is considered supersaturated with respect to HAP and FAP, and will cause ions to deposit on the tooth mineral until a new equilibrium is reached [41]. Interestingly, in the present study, the vast majority of the substances had low pH

Table 4. Multiple linear regression analysis of the changes in surface hardness (ΔSH) of all specimens after immersion in all substances.

ΔSH	Intercept		pH		Titrateable acidity		[Ca]		[P _i]	
	β	p	β	p	β	p	β	p	β	p
ΔSH_{2-0}	-135.70	<0.001	34.45	<0.001	-0.46	<0.001	2244.0	<0.001	ns	ns
ΔSH_{4-0}	-314.70	<0.001	69.32	<0.001	-0.53	<0.001	3885.0	<0.001	-5457.0	0.023

β -estimates and p-values are listed only for variables with a significant impact on ΔSH ;

[Ca] and [P_i]: calcium and phosphate concentrations, respectively;

ns = not significant.

doi:10.1371/journal.pone.0143957.t004

Table 5. Mean ± SEM (standard error of the mean) for surface hardness at baseline (SH_{baseline}), difference in surface hardness after the first (ΔSH₂₋₀) and both (ΔSH₄₋₀) erosive challenges, and the relative change in surface reflectivity (rSRI₄₋₀), for deciduous and permanent enamel samples.

Substance		Deciduous	Permanent	p-value
Mineral water (negative control)	SH _{Baseline}	509.5±19.6	517.7±11.7	0.280
	ΔSH ₂₋₀	-5.0±7.7	27.8±13.1	0.089
	ΔSH ₄₋₀	-11.1±12.0	19.1±12.6	0.089
	rSRI ₄₋₀	-15.6±11.0	1.6±5.2	0.436
Coca-Cola®	SH _{Baseline}	501.0±12.7	514.8±13.3	0.579
	ΔSH ₂₋₀	-90.2±11.3	-44.3±12.2	0.007*
	ΔSH ₄₋₀	-169.3±11.2	-139.8±10.7	0.075
	rSRI ₄₋₀	-83.0±2.0	-86.6±1.4	0.143

* Significant difference between deciduous and permanent enamel;

SH_{baseline}: surface hardness at baseline;

ΔSH₂₋₀: surface hardness decrease between baseline and the first erosive challenge;

ΔSH₄₋₀: surface hardness decrease between baseline and the second erosive challenge;

rSRI₄₋₀: relative difference in surface reflection intensity between baseline and the second erosive challenge.

doi:10.1371/journal.pone.0143957.t005

values (varying from 2.14 to 6.70) and negative (pK-pI)_{HAP} and (pK-pI)_{FAP} values, which prompted enamel to demineralize.

Although the (pK-pI)_{HAP} and (pK-pI)_{FAP} values are good indicators of whether enamel demineralization occurs, they are calculated based on the ionic composition of HAP and FAP of permanent enamel. Deciduous enamel, however, has a slightly different histological composition, so the (pK-pI)_{HAP} and (pK-pI)_{FAP} values presented in Table 1 can only serve as a guide to deciduous enamel dissolution. We therefore carried out the multiple regression analyses to verify which specific variables play a significant role in erosive demineralization of deciduous enamel.

Our results suggest that pH, titratable acidity, Ca²⁺ concentration and, to a lesser extent, P_i concentration in the substances can significantly influence erosion in deciduous enamel. Many studies have demonstrated how Ca concentrations in erosive solutions can modulate enamel demineralization [1, 12, 17, 44]. Higher Ca concentration in a given solution will increase its degree of saturation, thus lessening its erosive effect [45]. This is in line with our results, which showed that higher concentrations of Ca in the tested substances prompted significantly less erosive demineralization. P_i concentration, on the other hand, was not significant during the first erosive challenge (ΔSH₂₋₀), but only became significant after 4 min immersion in the substances (ΔSH₄₋₀). Similar results were also observed by Hemingway, Parker (46), who suggested that calcium ions are dissolved from the hydroxyapatite before phosphate ions, thus explaining the relationship between calcium concentration and erosion, and the lack of association between phosphate concentration and erosion. In addition, Lussi, Megert (22) argue that there are four species of P_i (H₃PO₄, H₂PO₄⁻, HPO₄²⁻ and PO₄³⁻) that could be present in a solution, but their concentrations are strongly influenced by the pH of the solution. At acidic pH, most P_i species are in the form of H₂PO₄⁻, and only a minute fraction is in the form of PO₄³⁻, which is the only species of importance in the ion activity of enamel [22, 46]. Therefore, at low pH, extremely high amounts of P_i would be necessary to increase the degree of saturation of a given solution to a level at which it would effectively hinder enamel demineralization [22]. In contrast to what was expected, the multivariate analysis in the present study shows that higher P_i concentrations are associated with a greater loss of SH. This is probably because, within the substances we have tested, the highest [P_i] values were measured in the highly

erosive substances, such as Coca-Cola[®], Pepsi[®], Rivella[®] Red, kiwi fruit and Gatorade[®], and this may be an expression that in some of these substances, like Coca-Cola[®] and Pepsi[®], there is a high phosphoric acid content, and, consequently, high Pi concentrations. It is, therefore, possible to conclude that (similarly to permanent enamel) P_i concentration does not play a significant role in erosive dissolution of deciduous enamel. Dissolution of deciduous enamel is, thus, strongly influenced by the Ca concentration, pH and titratable acidity of the substance.

Titratable acidity is a measure of the buffering of a solution, and it is directly related to the concentration of the undissociated form of the acid in a given substance [41]. The undissociated form of the acid is of considerable importance because this species has no charge and it is able to diffuse more readily into the near-surface layer of enamel. Once there, this species then dissociates acting as a proton (H⁺) carrier into the enamel mineral, and it maintains the acidic (undersaturated) condition that promotes further dissolution [23, 47]. So, higher titratable acidity values are strong indicators of higher concentrations of the undissociated species of the acid, which, in turn, lead to more enamel erosion.

Besides the effect of specific chemical factors associated with erosion in deciduous enamel, we also compared the effect of two substances (mineral water and Coca-Cola[®]) on both permanent and deciduous teeth. Our results showed no significant differences between the two types of teeth when the specimens were treated with mineral water. Treatment with Coca-Cola[®], however, caused a significantly greater loss of SH in deciduous enamel than in permanent enamel within the first 2 min (ΔSH_{2-0}), but no differences were observed in the total loss of SH after two erosive challenges (ΔSH_{4-0}). We, therefore, suggest that the initial erosive process may start differently in the two kinds of teeth, but also the lack of difference after the second erosive challenge could be due to the small sample size in the present study. In any case, conflicting results have been reported from studies on the dissolution pattern of deciduous and permanent enamel [4, 5, 48–52], so these differences should be further investigated.

In the present study, we show that various soft drinks, sour candies, sports drinks and energy drinks, and some fruits and fruit juices are able to cause enamel erosion. Thus, the excessive consumption of such substances can lead to substantial dental erosion, which may compromise patients' dentition for their entire lifetime [5].

It is important to note that, although the enamel samples were kept in saliva for 3 h to allow the formation of the salivary pellicle, all erosion challenges were made without saliva. More specifically, the sour candy and sour chewing gum were both diluted in water, and the tests on the erosive effect of these substances did not take into account the buffering effect of saliva. In a preliminary experiment carried out in our laboratory, we also dissolved sour chewing gum in human saliva and did the erosive challenge following the methods used in the present study. Dissolving the substance in 10 ml saliva caused no loss in enamel SH after 2 min or 4 min erosive challenge. However, Lagerlof and Dawes [53] showed that the maximum volume of saliva in the mouth before swallowing is 1.19 ml or 0.96 ml for males and females, respectively. So, when the sour chewing gum was dissolved in only 2 ml saliva in the preliminary experiment, we observed that even one drop of the solution was able to considerably decrease enamel SH after 2 min and 4 min challenge, which was probably related to the low pH (3.47) of the solution (unpublished results).

In this experiment, we used two parameters to measure enamel erosion: change in surface hardness (ΔSH) and surface reflection intensity (rSRI). Previous studies have shown that SRI is a viable additional method to measure the erosive demineralization of permanent enamel [37, 38, 54], because it highly correlates with Knoop surface microhardness, calcium release, and surface roughness [36]. In the present study, we were able to further demonstrate that SRI is significantly associated with surface hardness measured with Vickers nanoindentations.

Moreover, we also show that SRI is a suitable viable option to measure erosive demineralization on deciduous enamel.

In conclusion, we were able to corroborate the erosive potential of a broad range of drinks, foodstuffs and medications commonly consumed/used by children and young adolescents, and we show that erosive dissolution of deciduous enamel is significantly associated with pH, titratable acidity and calcium concentration in the solution. This study is an extensive overview, and it can be used to judge the erosive potential of many dietary substances and medications used by children.

Acknowledgments

The present study was supported by the Deutsche Gesellschaft für Zahnerhaltung (DGPZM-Wissenschaftsfonds). The authors show their gratitude towards G. Fischer and Prof. Häusler, Institute of Mathematical Statistics, University of Bern, for the statistical analyses, and to Brigitte Megert for her appreciated efforts in the laboratory. We also thank Dr. R.P. Shellis for his valuable comments on this manuscript.

Author Contributions

Conceived and designed the experiments: TSC AL. Performed the experiments: TSC. Analyzed the data: TSC AL. Contributed reagents/materials/analysis tools: AL. Wrote the paper: TSC AL.

References

1. Lussi A, Carvalho TS. Erosive tooth wear: a multifactorial condition of growing concern and increasing knowledge. *Monogr Oral Sci.* 2014; 25:1–15. doi: [10.1159/000360380](https://doi.org/10.1159/000360380) PMID: [24993253](https://pubmed.ncbi.nlm.nih.gov/24993253/).
2. Hunter ML, West NX, Hughes JA, Newcombe RG, Addy M. Erosion of deciduous and permanent dental hard tissue in the oral environment. *Journal of dentistry.* 2000; 28:257–63. doi: [S0300-5712\(99\)00079-2](https://doi.org/S0300-5712(99)00079-2) [pii]. PMID: [10722899](https://pubmed.ncbi.nlm.nih.gov/10722899/).
3. Rios D, Magalhães AC, Honório HM, Buzalaf MA, Lauris JR, Machado MA. The prevalence of deciduous tooth wear in six-year-old children and its relationship with potential explanatory factors. *Oral Health Prev Dent.* 2007; 5:167–71. PMID: [17977286](https://pubmed.ncbi.nlm.nih.gov/17977286/).
4. Kreulen CM, Van 't Spijker A, Rodriguez JM, Bronkhorst EM, Creugers NH, Bartlett DW. Systematic review of the prevalence of tooth wear in children and adolescents. *Caries research.* 2010; 44:151–9. doi: [10.1159/000308567](https://doi.org/10.1159/000308567) PMID: [20389070](https://pubmed.ncbi.nlm.nih.gov/20389070/).
5. Carvalho TS, Lussi A, Jaeggi T, Gambon DL. Erosive tooth wear in children. *Monogr Oral Sci.* 2014; 25:262–78. doi: [10.1159/000360712](https://doi.org/10.1159/000360712) PMID: [24993274](https://pubmed.ncbi.nlm.nih.gov/24993274/).
6. Lussi A, Schlueter N, Rakhmatullina E, Ganss C. Dental erosion—an overview with emphasis on chemical and histopathological aspects. *Caries research.* 2011; 45 Suppl 1:2–12. doi: [000325915](https://doi.org/000325915) [pii] doi: [10.1159/000325915](https://doi.org/10.1159/000325915) PMID: [21625128](https://pubmed.ncbi.nlm.nih.gov/21625128/).
7. Shellis RP, Ganss C, Ren Y, Zero DT, Lussi A. Methodology and models in erosion research: discussion and conclusions. *Caries research.* 2011; 45 Suppl 1:69–77. doi: [000325971](https://doi.org/000325971) [pii] doi: [10.1159/000325971](https://doi.org/10.1159/000325971) PMID: [21625135](https://pubmed.ncbi.nlm.nih.gov/21625135/).
8. Ganss C, Lussi A. Diagnosis of erosive tooth wear. *Monogr Oral Sci.* 2014; 25:22–31. doi: [10.1159/000359935](https://doi.org/10.1159/000359935) PMID: [24993255](https://pubmed.ncbi.nlm.nih.gov/24993255/).
9. Lussi A, Jaeggi T, Jaeggi-Schärer S. Prediction of the erosive potential of some beverages. *Caries research.* 1995; 29:349–54. PMID: [8521435](https://pubmed.ncbi.nlm.nih.gov/8521435/).
10. Järvinen VK, Rytömaa II, Heinonen OP. Risk factors in dental erosion. *Journal of dental research.* 1991; 70:942–7. PMID: [2045572](https://pubmed.ncbi.nlm.nih.gov/2045572/).
11. Hughes JA, West NX, Parker DM, Newcombe RG, Addy M. Development and evaluation of a low erosive blackcurrant juice drink in vitro and in situ. 1. Comparison with orange juice. *Journal of dentistry.* 1999; 27:285–9. PMID: [10193106](https://pubmed.ncbi.nlm.nih.gov/10193106/).
12. Larsen MJ, Nyvad B. Enamel erosion by some soft drinks and orange juices relative to their pH, buffering effect and contents of calcium phosphate. *Caries research.* 1999; 33(1):81–7. PMID: [9831784](https://pubmed.ncbi.nlm.nih.gov/9831784/).

13. O'Sullivan EA, Curzon ME. A comparison of acidic dietary factors in children with and without dental erosion. *ASDC J Dent Child*. 2000; 67:186–92, 60. PMID: [10902077](#).
14. Hunter ML, Patel R, Loyn T, Morgan MZ, Fairchild R, Rees JS. The effect of dilution on the in vitro erosive potential of a range of dilutable fruit drinks. *International journal of paediatric dentistry / the British Paedodontic Society [and] the International Association of Dentistry for Children*. 2008; 18:251–5. doi: [10.1111/j.1365-263X.2008.00917.x](#) PMID: [18435725](#).
15. Hunter L, Patel S, Rees J. The in vitro erosive potential of a range of baby drinks. *International journal of paediatric dentistry / the British Paedodontic Society [and] the International Association of Dentistry for Children*. 2009; 19:325–9. doi: [10.1111/j.1365-263X.2009.00975.x](#) PMID: [19320913](#).
16. Lussi A, Jäggi T, Schärer S. The influence of different factors on in vitro enamel erosion. *Caries research*. 1993; 27:387–93. PMID: [8242676](#).
17. Barbour ME, Parker DM, Allen GC, Jandt KD. Enamel dissolution in citric acid as a function of calcium and phosphate concentrations and degree of saturation with respect to hydroxyapatite. *European journal of oral sciences*. 2003; 111(5):428–33. PMID: [12974688](#).
18. Dugmore CR, Rock WP. A multifactorial analysis of factors associated with dental erosion. *British dental journal*. 2004; 196:283–6; discussion 73. doi: 4811041 [pii] doi: [10.1038/sj.bdj.4811041](#) PMID: [15017418](#).
19. Johansson AK, Lingström P, Imfeld T, Birkhed D. Influence of drinking method on tooth-surface pH in relation to dental erosion. *European journal of oral sciences*. 2004; 112:484–9. doi: [10.1111/j.1600-0722.2004.00172.x](#) PMID: [15560830](#).
20. Shellis RP, Finke M, Eisenburger M, Parker DM, Addy M. Relationship between enamel erosion and liquid flow rate. *European journal of oral sciences*. 2005; 113(3):232–8. doi: [10.1111/j.1600-0722.2005.00210.x](#) PMID: [15953248](#).
21. Jensdottir T, Bardow A, Holbrook P. Properties and modification of soft drinks in relation to their erosive potential in vitro. *Journal of dentistry*. 2005; 33(7):569–75. doi: [10.1016/j.jdent.2004.12.002](#) PMID: [16005796](#).
22. Lussi A, Megert B, Shellis RP, Wang X. Analysis of the erosive effect of different dietary substances and medications. *Br J Nutr*. 2012; 107:252–62. doi: S0007114511002820 [pii] doi: [10.1017/S0007114511002820](#) PMID: [21733310](#).
23. Shellis RP, Barbour ME, Jesani A, Lussi A. Effects of Buffering Properties and Undissociated Acid Concentration on Dissolution of Dental Enamel in Relation to pH and Acid Type. *Caries research*. 2013; 47(6):601–11. doi: [10.1159/000351641](#) PMID: [24061229](#).
24. Radlanski RJ, Renz H, Willersinn U, Cordis CA, Duschner H. Outline and arrangement of enamel rods in human deciduous and permanent enamel. 3D-reconstructions obtained from CLSM and SEM images based on serial ground sections. *Eur J Oral Sci*. 2001; 109(6):409–14. PMID: [11767278](#).
25. Shellis RP. Variations in growth of the enamel crown in human teeth and a possible relationship between growth and enamel structure. *Arch Oral Biol*. 1984; 29(9):697–705. PMID: [6594102](#).
26. Wilson PR, Beynon AD. Mineralization differences between human deciduous and permanent enamel measured by quantitative microradiography. *Arch Oral Biol*. 1989; 34(2):85–8. PMID: [2783050](#).
27. Sønju Clasen AB, Ruyter IE. Quantitative determination of type A and type B carbonate in human deciduous and permanent enamel by means of Fourier transform infrared spectrometry. *Adv Dent Res*. 1997; 11(4):523–7. PMID: [9470513](#).
28. STACK MV. Variation in the organic content of deciduous enamel and dentine. *Biochem J*. 1953; 54(2): xv. PMID: [13058902](#).
29. Ganss C, Klimek J, Giese K. Dental erosion in children and adolescents—a cross-sectional and longitudinal investigation using study models. *Community Dent Oral Epidemiol*. 2001; 29(4):264–71. PMID: [11515640](#).
30. Harding MA, Whelton HP, Shirodaria SC, O'Mullane DM, Cronin MS. Is tooth wear in the primary dentition predictive of tooth wear in the permanent dentition? Report from a longitudinal study. *Community Dent Health*. 2010; 27(1):41–5. PMID: [20426260](#).
31. Zero DT, Rahbek I, Fu J, Proskin HM, Featherstone JD. Comparison of the iodide permeability test, the surface microhardness test, and mineral dissolution of bovine enamel following acid challenge. *Caries research*. 1990; 24:181–8. PMID: [2364403](#).
32. Chen PS, Toribara TY, Warner H. Microdetermination of phosphorus. *Analytical chemistry*. 1956; 28:1756–58.
33. Larsen MJ. An investigation of the theoretical background for the stability of the calcium-phosphate salts and their mutual conversion in aqueous solutions. *Archives of oral biology*. 1986; 31:757–61. PMID: [3479063](#).

34. McCann HG. The solubility of fluorapatite and its relationship to that of calcium fluoride. *Archives of oral biology*. 1968; 13(8):987–1001. PMID: [5250212](#).
35. McDowell H, Gregory TM, Brown E. Solubility of $\text{Ca}_5(\text{PO}_4)_3\text{OH}$ in the system $\text{Ca}(\text{OH})_2\text{-H}_3\text{PO}_4\text{-H}_2\text{O}$ at 5, 25 and 37°C. *J Res Natl Bur Stand*. 1977; 81:273–81.
36. Rakhmatullina E, Bossen A, Hoöschele C, Wang X, Beyeler B, Meier C, et al. Application of the specular and diffuse reflection analysis for in vitro diagnostics of dental erosion: correlation with enamel softening, roughness, and calcium release. *Journal of biomedical optics*. 2011; 16:107002. doi: [10.1117/1.3631791](#) PMID: [22029364](#).
37. Lussi A, Bossen A, Höschele C, Beyeler B, Megert B, Meier C, et al. Effects of enamel abrasion, salivary pellicle, and measurement angle on the optical assessment of dental erosion. *Journal of biomedical optics*. 2012; 17:97009–1. doi: [10.1117/1.JBO.17.9.097009](#) PMID: [23085926](#).
38. Brevik SC, Lussi A, Rakhmatullina E. A new optical detection method to assess the erosion inhibition by in vitro salivary pellicle layer. *Journal of dentistry*. 2013; 41(5):428–35. doi: [10.1016/j.jdent.2013.02.011](#) PMID: [23454333](#).
39. Wetton S, Hughes J, West N, Addy M. Exposure time of enamel and dentine to saliva for protection against erosion: a study in vitro. *Caries research*. 2006; 40(3):213–7. doi: [10.1159/000092228](#) PMID: [16707869](#).
40. Stiefel DJ. Characteristics of an in vitro dental pellicle. *Journal of dental research*. 1976; 55(1):66–73. PMID: [1060664](#).
41. Shellis RP, Featherstone JD, Lussi A. Understanding the chemistry of dental erosion. *Monogr Oral Sci*. 2014; 25:163–79. doi: [10.1159/000359943](#) PMID: [24993265](#).
42. ten Cate JM, Buijs MJ, Damen JJ. pH-cycling of enamel and dentin lesions in the presence of low concentrations of fluoride. *European journal of oral sciences*. 1995; 103:362–7. PMID: [8747671](#).
43. Hughes JA, West NX, Parker DM, van den Braak MH, Addy M. Effects of pH and concentration of citric, malic and lactic acids on enamel, in vitro. *Journal of dentistry*. 2000; 28:147–52. PMID: [10666974](#).
44. Attin T, Meyer K, Hellwig E, Buchalla W, Lennon AM. Effect of mineral supplements to citric acid on enamel erosion. *Archives of oral biology*. 2003; 48:753–9. PMID: [14550377](#).
45. Dawes C. What is the critical pH and why does a tooth dissolve in acid? *J Can Dent Assoc*. 2003; 69:722–4. PMID: [14653937](#).
46. Hemingway CA, Parker DM, Addy M, Barbour ME. Erosion of enamel by non-carbonated soft drinks with and without toothbrushing abrasion. *British dental journal*. 2006; 201(7):447–50; discussion 39; quiz 66. doi: [10.1038/sj.bdj.4814073](#) PMID: [17031352](#).
47. Featherstone JD, Lussi A. Understanding the chemistry of dental erosion. *Monogr Oral Sci*. 2006; 20:66–76. PMID: [16687885](#).
48. Amaechi BT, Higham SM, Edgar WM. Factors influencing the development of dental erosion in vitro: enamel type, temperature and exposure time. *J Oral Rehabil*. 1999; 26:624–30. PMID: [10447814](#).
49. Hunter ML, West NX, Hughes JA, Newcombe RG, Addy M. Relative susceptibility of deciduous and permanent dental hard tissues to erosion by a low pH fruit drink in vitro. *Journal of dentistry*. 2000; 28:265–70. doi: [S0300-5712\(99\)00074-3 \[pii\]](#). PMID: [10722900](#).
50. Johansson AK, Sorvari R, Birkhed D, Meurman JH. Dental erosion in deciduous teeth—an in vivo and in vitro study. *Journal of dentistry*. 2001; 29:333–40. PMID: [11472805](#).
51. Lippert F, Parker DM, Jandt KD. Susceptibility of deciduous and permanent enamel to dietary acid-induced erosion studied with atomic force microscopy nanoindentation. *European journal of oral sciences*. 2004; 112:61–6. PMID: [14871195](#).
52. Magalhães AC, Rios D, Honório HM, Delbem AC, Buzalaf MA. Effect of 4% titanium tetrafluoride solution on the erosion of permanent and deciduous human enamel: an in situ/ex vivo study. *J Appl Oral Sci*. 2009; 17:56–60. PMID: [19148407](#).
53. Lagerlöf F, Dawes C. The volume of saliva in the mouth before and after swallowing. *Journal of dental research*. 1984; 63(5):618–21. PMID: [6584462](#).
54. Rakhmatullina E, Bossen A, Bachofner KK, Meier C, Lussi A. Optical pen-size reflectometer for monitoring of early dental erosion in native and polished enamels. *Journal of biomedical optics*. 2013; 18(11):117009. doi: [10.1117/1.JBO.18.11.117009](#) PMID: [24247749](#).